

APPENDIX I

This application is a continuation-in-part of application Serial No. 07/730,972, filed July 26, 1991, the disclosure of which application is expressly incorporated herein by reference.

BACKGROUND OF THE INVENTION

Field of the Invention ~~A METHOD OF MANUFACTURING AN ARTIFICIAL CASING AND AN ARTIFICIAL CASING PRODUCT~~

The invention relates to a method of manufacturing a fibrous cellulose casing and a casing manufactured by this method.

Description of Prior Art

~~Artificial~~ Generally, ~~artificial~~ cellulose casings, which are alternatively described as fibrous cellulose casings, or simply as fibre and fiber reinforced casings, et cetera, are manufactured from a long fibre paper base and regenerated cellulose from viscose, that is the soluble sodium cellulose xanthate derivative of cellulose. Before subjecting the paper base to this viscose treatment, or impregnation, it is first wet
15 fiber paper base impregnated with cellulose which has been regenerated from viscose. Prior to viscose impregnation the paper is wet strengthened by the paper manufacturer, also using cellulose regenerated cellulose from viscose, or alternatively using other wet strengthening materials such as polyamide epihalohydrin resins, polyvinyl alcohol, hydroxyethyl cellulose,

~~and various synthetically produced latices, et cetera, lattices~~
~~either used singly or 20 in combination one with another, for~~
~~example combining regenerated cellulose from viscose and a~~
~~polyamide epichlorohydrin resin such as Kymene (Kymene is a~~
~~registered trademark of the Hercules Company of the USA), or~~
~~using mixtures of these.~~ The chief reason for conferring this
wet strength ~~on the part of the paper manufacturer~~ is to enable
the paper to retain its integrity and withstand the subsequent
heavy impregnation with the strongly alkaline viscose, which is
applied by the casing manufacturer, and the subsequent strongly
acidic cellulose coagulation and regeneration stage, ~~when by~~
~~which~~ the casing is made.

~~And whereas~~ ~~Whereas~~ the paper manufacturer may apply
only one to six percent regenerated cellulose from viscose and/or
other wet-strengthening resins calculated on the basis of total
~~fibre~~ ~~fiber~~ weight, to provide the necessary wet strength, the
casing manufacturer usually applies a quantity of viscose of two
to three times the total weight of the paper to construct the
casing. ~~In the case of the paper, which may weigh 21 g/m² in~~
~~total, only 0,21 to 1,26 g/m² would therefore comprise~~
~~regenerated cellulose from viscose, and the rest fibre, for~~
~~example, whilst~~ ~~For example, in the case of paper which weighs 21~~
~~g/m²,~~ the casing manufacturer would add ~~a further~~ ~~an additional~~
42 to 63 g/m² g/² regenerated cellulose from viscose in making
the casing ~~of,~~ ~~amounting to a~~ total cellulose weight 63 to 84

g/m². ~~In the commercial situation this fibre-Fiber-~~ reinforced cellulose ~~of this example~~ would be ~~commercially~~ prepared or plasticized with a quantity of 20 to 25 percent glycerol and moisturized with 5 to 10 percent water, to prevent it drying out and becoming brittle prior to use, ~~to achieving~~ an overall basis weight ~~in the example~~ given of between 78,8 and 119 g/m².

~~It is also worth pointing out that the~~ ~~The~~ process for making the paper and the process for making the casing are very different ~~in a number of other important ways, for example, in terms of.~~ For example, imparting wet-strength to the paper, ~~this~~ is a relatively easy and inexpensive stage for the paper manufacturer, ~~which can and may~~ be carried on in-line with paper-making, ~~but,~~ whereas wet strengthening is totally impracticable and prohibitively expensive for the casing manufacturer who requires the paper fully wet-strengthened from the outset ~~of the casing manufacturing process.~~

The ~~fibre-furnish~~ ~~fiber~~ of the paper substrate used to make fibrous casing is usually a carefully selected choice of abaca ~~fibres~~ ~~fibers~~, also known as manila hemp ~~fibres~~ ~~fibers~~, grown in either the ~~Phillipines~~ ~~Philippines~~ or Ecuador, which are subjected to a chemical pulping treatment to remove ~~noncellulosic~~ ~~non-cellulosic~~ material and to soften the ~~fibres~~ ~~fibers~~ for paper-making. A ~~part~~ ~~portion~~ of this ~~fibre~~ ~~fiber~~ may be provided by alternative plant ~~fibre~~ ~~fiber~~ such as sisal, jute, or wood pulp, etc., but not without affecting the casing strength

characteristics, usually in a negative way. Papers so prepared, of basis weight between 17 and 28 g/m², are well known in the art for manufacturing fibrous cellulose casings, in the range of size typically from 32 to 165 mm in diameter, or even larger, and usually the basis weight of the paper is increased, for example, from 17 to 19 g/m², from 19 to 21 g/m², from 21 to 23 g/m², and so on in stages, as diameter increases and the need for greater strength increases, that. This is, since because the weight of the sausage product increases exponentially as a function of a squaring of the radius of the sausage.

The casing manufacturer's process usually involves unwinding the paper, supplied in rolls by the paper manufacturer, from an unwind stand, by drawing and forming the paper into the shape of a tube with overlapping margins. The paper is drawn continuously about its longitudinal axis, by bending actions with the assistance of metal guides, and while sticking the margins together using viscose just ahead of the fuller immediately prior to the impregnation with the bulk viscose which makes up the reinforced cellulose wall of the casing.

The composition of this the aqueous viscose solution may vary but an varies but may comprise, for example of, 7 to 8 weight percent (wt-%) cellulose, as 30-33 percent (wt-%) sodium cellulose xanthate of 30 to 33% xanthate sulphur, 4 to 5 wt-% 5 percent (wt-%) sodium hydroxide and rest water, with a ball-fall viscosity of 50 to 70 seconds (130 mg steel ball of 3,175 mm

diameter over a distance of 20 cm) and a. A Hottenroth ripening (salt) index of 4 to 5 at a temperature of 25 to 30 degrees Celsius may be regarded typical.

Once impregnated, the ~~cellulose of the~~ viscose is coagulated and regenerated into cellulose by passing the impregnated tube through a ~~sulphuric~~ sulfuric acid and salt bath, usually containing ammonium and sodium sulphate mixtures, followed by various acid and water wash baths to complete the regeneration and remove all remaining sulphur from the viscose. Acid strength may vary ~~but from~~ 40 to 60 g/liter g/l and a salt strength between 180 and 260 g/l with ~~reset~~ respect to sodium sulphate and between 10 and 50 g/l with respect to ammonium sulphate may be regarded typical. Before drying this ~~fibre~~ fiber-reinforced tube it is usually passed through a bath containing a dilute aqueous glycerol solution, of 10 to 20 percent strength, to act as a plasticizer for the cellulose. Drying is ~~preferably~~ conducted ~~preferably~~ with the casing in an inflated condition, ~~and tension,~~. Tension throughout the casing machine, is maintained such that the diameter of the casing at the outset, that is the diameter provided by the original width of paper in the roll, less that used for overlapping, is reproduced as far as possible in the finished casing tube.

~~The viscose~~ Viscose impregnation may be effected by pouring the viscose onto the outer surface of the paper substrate, well ahead of the acid bath, in order to ensure that

the paper is thoroughly impregnated prior to regeneration of the cellulose with acid, ~~or alternatively.~~ Alternatively, the paper-impregnation stage may be effected ~~from~~ accomplished with a specially constructed viscose die, wherein the viscose is presented under pressure, through the lips of the die, directly onto the outer surface of the paper base, or substrate, ~~whilst being.~~ The paper is temporarily supported during transit across these the ??? lips, by a metal ring or cylinder, the gap between ring and die being such as to allow the paper to pass unimpeded, but not of such a width as to fully dissipate the pressure of the viscose before impregnating the paper, ~~this impregnation being.~~ Impregnation is completed by ~~continuing the passage of~~ passing paper between the die and the supporting ring for some distance within fixed gap dimensions, and thereafter passing the paper for some distance unsupported free through air before entering the acid coagulation and regeneration bath.

~~In the prior art and particularly the prior art insofar as that which pre-dates the original specification of the application in the present family of specifications, first filed in December 1989, the results of such impregnations are invariably very two-sided~~ Such impregnations may result in a product in which the two surfaces of the paper are unequally viscosed, only one side being fully impregnated owing to the resistance to penetration of papers of 17 g/m² and greater, ~~the~~ greater the paper weight usually the equating to greater the

~~resistance, and the greater the two-sidedness to viscoses, which, at low velocity, are characterized by relatively high solution viscosity.~~

In still another variant, viscose may be supplied to both sides of the paper simultaneously in order to effect a so-called double-viscose -coating, ~~to ensure.~~ This ensures that the paper reinforcement is disposed as far as possible within, and properly covered by viscose, prior to coagulation and regeneration of the cellulose.

Cellulosic tubings produced in these various ways are tough and strong and have low stretch characteristics. For these reasons they may be used as containers, or casings, for sausages, meats, or other articles of food, particularly in applications where size, in terms of diameter control, is a critical parameter, and where a highly mechanized sausage stuffing plant places high demands for consistency of performance, and where strength with toughness is at a premium.

~~Because of ever greater demands of packaging machinery with higher through-put rates, and in the case of blister-packaged goods, tighter size control of sausage diameters to meet minimum weight criteria, that is to contain so-called give-away meat levels; or alternatively the exact size requirements of subsequent vacuum packaging equipment, where a chub of product will be subject to maximum length and diameter tolerances in order to fit pre-sized cartons, or other containers for~~

~~distribution and retailing. Whilst~~ While exact size is achieved from a fibrous casing exhibiting low stretch, this also means that for differences in sausage diameter of only a few millimeters, another size of viscose die has to be used, ~~with all that this entails in terms of.~~ This entails additional costs for the separate inventorying on the part of the paper supplier, the casing manufacturer and the sausage maker, ~~etc~~ and for additional dies.

In parallel with the development of ever more demanding packaging equipment in the technologically ~~more~~ advanced countries, which ~~in turn~~ as described above has placed ever greater demands on the casing producer to make tougher, stronger and more-size consistent ~~easings,~~ casing (which demands have been met by the fibrous cellulose casing ~~manufacturers~~ manufactures), collagen and cellophane casings, or pure cellulose casings unreinforced by a fibrous substrate, have been developed for less critical market areas where exact size, ~~linked to high through-put rate of product based on highly mechanized stuffing equipment,~~ is not the first or most important selection criterion, but rather flexibility of use and unit cost, ~~have been~~ are more important considerations.

~~In this way it can be imagined that these parallel~~ These developments have been divergent rather than convergent, which is to say a gap exists between the two ~~was increasing~~ where, for types of casing markets. For example, a highly

flexible casing ~~but~~ of consistent though by no means exceptional strength was ~~maybe~~ required for mechanized stuffing machinery, ~~but~~ without subsequent packaging equipment also demanding exact size. In this example collagen ~~casing~~ would have provided the right price level but would not have provided the strength and associated low ~~product~~ ~~produce~~ breakage rate characteristic of a fibrous casing, and the fibrous casing would be considered over-engineered and too costly.

~~In recent years this gap has been filled with what may be regarded a hybrid which sought to combine something of the consistency of properties of the fibrous casing but with the elasticity equal to if not superior than that of collagen, whilst being price competitive. The first patent application in which exceptional elasticity was combined with low cost in a fibrous casing, was the specification previously referred to and filed in late 1989. In this application abaca (manila) paper wet-strengthened using regenerated cellulose from viscose, in a basis weight of no more than 15 g/m², and preferably 13 g/m², was used as the long fibre reinforcement to produce a lightweight fibrous casing product of exceptional elasticity properties combined with an exceptional strength to weight ratio, possessing an exceptionally smooth inner surface which, when combined with the casing's lighter weight, provided a means also for significantly reducing salami processing times as an added benefit, that is from say five weeks to four weeks compared to prior art fibre-~~

- Moved to
PP. 17-18
in substantial
part.

~~reinforced casings. In the present application which may be regarded a continuation application of this first one in the sense that it seeks to achieve the same collection of unique properties, principally combining high elasticity at a good weight to strength ratio in an overall lightweight construction, which will still allow it to compete in market areas prior to 1989 essentially unavailable to the fibrous cellulose casing, but more traditionally served by collagen or pure cellulose casings, the problem has been to use an alternative paper base which does not rely only on viscose, to provide the initial wet strength by the paper manufacturer for subsequent viscosing operations by the casing manufacturer, but which instead relies on alternative wet-strengthening systems not incorporating viscose. Now, as will be apparent from a study of the prior art before 1989 insofar as commercially viable fibrous casing manufacture is concerned, the problems quite often were related to~~ Prior art improvements in casing manufacture usually focused on improving the wet strength or reducing the variability of strength of paper substrates typically of the order of 20 to 23 g/m², in order so that a more consistent casing size or strength could be achieved. The use of polyamide-epihalohydrin resin and cationic polyethylene imine resin to provide an improvement in the alkaline wet tensile paper properties, in the US patent U.S. Patent No. 4,222,821 is one such example.

— moved to
pp. 17-18
in
substantial
part

~~This application does not relate to the manufacture of fibrous cellulose tubings as such but rather to the manufacture of a paper substrate of improved performance for subsequent conversion into fibrous casing. Another example is US Patent No.~~ Another example is U.S. Patent 3,433,633 which seeks to improve the quality of the viscose-bonded or wet-strengthened manila hemp paper substrate, for subsequent fibrous cellulose casing manufacture, by using cellulose derivatives of high viscosity to provide stronger casings. The implication according to US of U.S Patent Specification 3,433,633 is clearly that the existing -22,7 22.7 g/m² substrates lack sufficient strength, and therefore teach away from the use of lower substrate paper basis weights. Since 1989, significantly, papers.

In recent years patent specifications have appeared which chart the progress of applying alternative sought to apply wet strengthening systems, other than those based on viscose, to treat the fibrous casing abaca fibre paper substrate, that is, using abaca fibers by employing a variety of resin-based systems. US U.S. Patent 5,063,104 filed early in 1990 is one such an example which also high-lights highlights how paper physical properties of paper may be affected in a dramatic or significant manner depending upon what wet strengthening binder or bonding method is substituted for viscose. One property which is affected significantly, and adversely so, insofar as the requirements of the present applicants' original specification of

~~the present application is concerned, adversely affected by the use of resins as wet-strengthening agents~~ is paper stretch or elongation. Reductions of up to 20 to 50 percent for wet elongation ~~from the levels obtained for viscose bonding of the paper were obtained in US 5,063,104, and fibrous, as compared to elongation properties for viscose bonded paper, were demonstrated in this patent.~~ Fibrous casing elongation is very much dependent on the substrate paper's elongation.

~~The present application describes a method to overcome the problems associated with reduced paper stretch which arises from the paper manufacturing process and process chemistry, that is insofar as the paper is treated, in order to make it strong and resistant to alkalis and acids in the wet state, for the casing manufacturer's purposes, as opposed to problems of say a self-inflicted nature on the part of the casing manufacturer. Now in In order to make fibrous casings of ever-increasing diameter we have seen in the art prior to 1989 that the requirement for and therefore ever greater strength was met by, the use of ever-increasing substrate paper basis weights and/or by the use of strength adjuncts adjuncts to complement that offered by the viscose bond alone, for bonded casings, typically using manufactured from paper having weights of 17 g/m² and greater, whilst exceptionally the original specification presented paper substrates of 13 to 15 g/m² to make a range of light weight casings from 32 mm diameter up to 105 mm and indeed succeeded in~~

Moved to P.18
in Substantial
part.

~~extending the size to include casings with diameters up to 165 mm. In reversing this~~ had been required. This trend of using heavier weight paper to make wider diameter casings, ~~that is reducing paper basis weight whilst reducing casing diameter,~~ has as a corollary the fact that small diameter casings may be manufactured using papers with lower basis weight. However, in using low weight papers a limit is approached by virtue of the fact that a certain minimum paper strength in both dry and wet states is required ~~in order so~~ that the paper will withstand draw tension ~~so that applied when it may be is~~ unwound from its roll (dry strength), and thereafter possess sufficient wet strength, following impregnation with the viscose of the casing manufacturer's process, so that it may successfully be converted into the casing product (wet strength).

Following the impregnation, the substrate paper tube, now saturated with viscose, has minimum strength and spends much of its time during its subsequent passage through the casing manufacturing machine as a flattened tube ~~the~~. The greater the surface area of this tube over turn-over rolls, which are used in the machine to convey it, and not all of which are necessarily driven, the less paper strength is required ~~to convey it~~. These requirements for strength may be considered at variance: ~~the larger the casing the easier it can be converted into casing~~ Manufacture of larger diameter casings using lighter weight substrate paper, ~~but performing less robustly by the sausage-~~

~~maker, whilst the narrower casing made with heavyweight paper possesses adequate strength for the casing manufacturer's purposes, but~~ is relatively easy due to the large surface areas involved, but these casings do not perform robustly due to the high strength demands associated with large diameter casings compared to the low strength of the lighter-weight papers. Conversely, manufacture of narrower casings must be accomplished with heavier paper due to the relatively low surface areas involved, but narrow diameter casings may provide more strength than is required of the sausage-maker and be considered over-engineered, ~~an and expensive alternative as a result.~~

In order to obtain the desirable physical property mix of the ~~subject casings of to original specification present invention~~ using resin-bonded papers ~~of inferior, that is, having~~ lower, wet extension or elongation properties compared to ~~substrate papers bonded with regenerated cellulose provided by viscose, that is~~ papers wet strengthened with viscose (prior to the viscose impregnation applied by the casing manufacturer), it ~~has had~~ been found that substrate paper weights need to be reduced from 13 to 15 g/m² to preferably 10 to 12 g/m². ~~Unfortunately this development at the same time takes the manufacturing process for the casing into uncharted water~~ insofar as ~~when manufacturing processes are employed. Use of these light papers in conventional viscose dies are usually~~ (engineered with robust and heavy papers in mind, ~~where moderate paper web tensions applied by drive rollers exerted over distances of~~

~~several meters do not usually cause excessive so-called "necking-in" of the tube, that)~~ causes an undesirable "necking-in" of the casings necking-in is brought about by a simultaneous extension of the tube in its longitudinal direction and a commensurate shrinkage in its transverse direction, which ~~is to say tube reduces the diameters are reduced of the casings~~ from those defined by the die size. ~~And unless~~ Absent steps are taken to overcome this obstacle, the whole process of reducing paper weight to obtain more casing trans-directional extension becomes self-defeating. In order to overcome these difficulties using while without reengineering the viscose dies ~~normally used and designed for much heavier paper substrates, of say 21 g/m² of the prior art, it is possible to slow down the whole operation but this approach is not always convenient, and in certain cases may be considered somewhat self-defeating.~~ it is necessary to slow down the entire casing manufacturing operation thereby to reduce stress on the lightweight paper. This approach is generally not convenient or economically feasible in that additional costs are likely to be incurred as a result of slow processing.

Description of the Drawings

The invention is now described in more detail with reference to the accompanying drawings in which:

~~Figure 1 shows how the~~ Fig. 1 is a schematic representation of the apparatus by which tubing is manufactured by first forming the substrate paper into a tube and impregnating

it with viscose at a die ahead of the acid coagulation and cellulose regeneration bath.

~~Figure 2 shows~~ Fig. 2 depicts the viscose die of Fig. 1 enlarged. Figure in greater detail.

Fig. 3 is a diagram showing the relationship between casing elasticity, paper weight and paper wet CD stretch of tubing known tubing in the art and tubing made according to this invention.

~~Accordingly, for the new generation of~~ Summary of the Invention

The invention is a method of manufacturing lightweight fibrous casings constructed of abaca paper substrates suitably wet-strengthened using viscose, or viscose and resin, and subsequently viscosed a second time by the casing manufacturer, ~~that is in the original specification, a new arrangement of viscose die and the casings made by this method.~~

The method of this invention employs an arrangement of a die and related apparatus which has been developed for the purpose of accomplishing single-sided viscosing, ~~which allows casing machine speeds to be increased over those operating for the casing examples in the original specification, at today's commercial levels, employed for conventional fibrous casing lines, whilst at the same time providing a~~ of light weight paper substrates at increased machine speeds. The die arrangement of this invention provides superior impregnation of viscose during the casing manufacturing stage, ~~to ensure~~ ensures smooth surfaces

of both easing the inner and outer casing surfaces is obtained, to render and renders the need for double-sided viscosing unnecessary, or undesirable, in the case of these new generation light weight casings. When used for the subject casings of the present application, this. This new arrangement of viscose die seeks to minimize minimizes drag upon impregnating the paper matrix with viscose, and, during the subsequent crucial period before coagulation of the viscose and its regeneration into cellulose has been completed, to the extent of thereafter permitting, so as to permit the casing to be stretched but not irreversibly

This is Detailed Description of Preferred Embodiments

The present invention combines of the consistency of properties of the fibrous casing with the elasticity equal to if not superior than that of collagen casing, while being price competitive. Abaca (manila) paper wet-strengthened using regenerated cellulose from viscose, in a basis weight of no more than 15 g/m², and preferably 13 g/m², is used as the long fiber reinforcement to produce a lightweight fibrous casing product of exceptional elasticity properties combined with an exceptional strength to weight ratio, possessing an exceptionally smooth inner surface.

Another embodiment of this invention relies on alternative wet-strengthening systems not incorporating viscose alone.

- Mould from
pp. 9-10
is substantial
part.

Because the present invention combines high elasticity at a good weight to strength ratio it will be able to compete in markets which were previously unavailable to the fibrous cellulose casing, and were more traditionally served by collagen or pure cellulose casing. The present application describes a method to overcome the problems associated with reduced paper stretch which arises from the paper manufacturing process and process chemistry, that is insofar as the paper is treated, in order to make it strong and resistant to alkalis and acids in the wet state for the casing manufacturer's purposes.

The present application's specification presents paper substrates of 13 to 15 g/m² to make a range of light-weight casings of about 32 mm diameter and greater. The goals of the present invention are achieved by minimizing the viscoosed wet strengthened paper substrate-metal surface contact in the area of the die, and by judicious overfeeding of the paper to the inlet side of the die on the one and hand, while at the same time carefully controlling the paper draw or tension on the impregnated web on the lead-out side of the die on the other, to minimize the longitudinal extension of the substrate paper and obtain the subject paper embedded within the casing in a non-extended fashion. This new arrangement of viscose die, designed expressly for the purpose of impregnating lightweight papers in the 10 to 15 g/m² range, at line speeds faster than those previously used for treating lightweight paper substrates, will

Moved from
p. 9-10
in substantial
part

Moved from
p. 12
in substantial
part

now be described with reference to Figure 1, against the background of those of the prior art which are regarded less than ideal for the subject casings.

Paper, providing the casing substrate, is unwound from rolls delivered by the paper supplier in lengths of for example 10,000 meters, that is from paper rolls of weights from about 10 to 50 kg. With the assistance of paper unwind rolls, some of which are driven, the substrate paper is fed to the viscose die over metal guides at ~~7, see diagram~~, where it is formed into a tube, in such a manner as to keep the die overfed with paper. The dimensions of the die are ~~regarded~~ critical for the reasons previously indicated, ~~that is i.e.,~~ since they impinge on paper extension properties which are affected by frictional forces, or drag, in the region of the die directly following viscose-impregnation, and an important objective of the present application is to reduce the effects of such frictional forces to a minimum. (Many of the die arrangements described in the prior art appear without dimensions, except insofar as drawings of dies are presented ~~but actual.~~ Actual dimensions are often absent, and.

~~And~~ where actual dimensions have been given, most notably in connection with so-called double-sided viscosing methods, which are not directly relevant to the present application, the ranges have been so wide as to describe non-critical situations. ~~US).~~

U.S. Patent Application Nos. 2,105,273 and 2,144,900 which

appeared January 8th 8, 1938 and January 24th 24, 1939 are good examples of the former which is for many years undoubtedly represented the state of the art of viscose die technology and indeed of fibrous casing manufacture. Sizing the dies of these specifications from their drawings suggests suggested they are of a low viscose pressure type since drawings suggest they are of a low viscose pressure type since the gap between the lips list of the die, corresponding to dimension 1 of the dies of the present specification would be of the order of 2,5 to 3,0 of 2.5 to 3.0 mm for a die to produce a 45 mm diameter casing.

~~Compared to dies used for many years by the present applicants the~~ The die described in these prior art specifications would be regarded as of robust design and suited usually suitable to the requirements of substrate papers in the 21 to 28 g/m² basis weight interval, which characterized fibrous casing manufacture in the era under review. Such dies would not be expected to give rise to good viscose penetration of the paper substrate, and so it is not surprising that subsequent improvements tended to focus on higher pressure die technology, using narrower gaps between the lips of the dies to increase viscose velocities, and increasingly to focus attention on double-sided viscosing as in, for example US U.S. 3,709,720, where the two impregnations with viscose are conducted within a second or a fraction of a second of each other and where Kindl, its author, claims the apparatus such as that used in US U.S.

2,105,273 for single-sided viscosing, required adequate time for the viscose to penetrate the paper properly before beginning the cellulose coagulation and regeneration stages under acid, otherwise the poor penetration would have resulted in casings being produced of inferior strength and poorer transparency than where effective saturation of the tube with viscose is first carried out.

~~An objective of the~~ ~~The~~ present invention ~~has been to~~ ~~retain~~ ~~retains~~ the excellent viscose penetration properties offered by the higher pressure type of die, and thereby ~~contain~~ ~~contains~~ distances between die and coagulation baths to short distances of the order of ~~0,3~~ 0.3 to ~~0,6~~ 0.6 meters, but only by relying on the need for a single ~~sided~~ viscose impregnation in order to reduce drag between viscosed paper substrate/metal surface contact/viscose pressure forces in the area of the die involved with viscose penetration, that is at the lips of the die and directly following them. In order to reduce the effects of drag, paper lead-in and lead-out distances into and out of the area of viscose issue, from the lips of the die, have been kept small, and balanced with machine line speeds and paper basis weight, in an attempt also to achieve the best possible viscose penetration. Accordingly, based on a fixed gap through which the viscose passes of ~~0,5~~ 0.5 mm, dimension 1 in Figure 1, the gap between the lips of the die, both upwards and downwards in cylindrical disposition with the formed tube of paper and the

face of the supporting metal ring or cylinder, ~~a~~"c", is fixed at ~~0,5~~ 0.5 to ~~0,7~~ 0.7 mm and preferably ~~0,55~~ 0.55 to ~~0,60~~ 0.60 mm and regarded critical within the context of the other specified dimensions. This has been found suitable to accommodate the relatively narrow range of substrate paper thicknesses, in the range 50 to 80 ~~um~~ μm , and generally thinner than those of the prior art for 17 to 28 g/m² substrates.

It will be appreciated that the effects of frictional factors increase as basis weight decreases, ~~whilst~~ while increased line speeds, which of necessity involve also increased draw or paper web tension, directly following viscose impregnation, since the draw is applied after the turn-over roll, ~~a~~"d" in Figure 1, also increase the effects of friction. The paper lead-in distance, ~~dimension 3, Figure 1~~ has accordingly been set at between 10 mm and 5 mm in one preferred arrangement of the dies of the present application, ~~dimension 3, Figure 1,~~ depending on the basis weight of paper impregnated and the line speed used. With reasonable line speed running, viscose flow from the point of issue from the lips of the extrusion die, is predominantly downward with the paper, making a seal backwards from the die upper lip ~~a~~"a" between paper ~~b~~"b" and paper support ~~a~~"c" with viscose. Similarly, on the lead-out side of the die, the lip width, dimension 2 in Figure 1, of the present application, should be between 10 mm and 2 mm in conjunction with a paper support ring, ~~a~~"c" in Figure 1, of 10 to 25 mm in

length, supporting the paper on its approach to the area of influence of the die's upper lip and extending to a distance horizontal ~~±~~ 1-2 mm with the lower end of the lower lip in order to contain frictional effects, the combined result of ~~paper~~ ~~viscose/metal~~ ~~paper/viscose/metal~~ contact-surface interactions which in turn interact with line speed and paper tension effects.

Despite the reduced metal surface contact of the lower lips of these new die arrangements and also of the metal ring paper support element, herein described, together with relatively short distances for the impregnated web to travel before entering the acid bath, but conducted at acceptably high speeds from the commercial standpoint as indicated elsewhere, no loss of quality is observed for the subject ~~fibre~~ ~~fiber~~ reinforced casings either in terms of transparency, strength properties or otherwise. Indeed, rather the converse can be claimed and casings result which possess exceptionally good transparency, exceptionally high weight to strength ratios, and where there exists good evidence by way of Bendtsen smoothness measurements to suggest the physical property mix of the subject casings are of a superior order. So specified the die may be used to advantage to produce the subject casings in the paper basis weight interval from 15 ~~down~~ to 10 g/m² and ~~whilst~~ ~~while~~ the longer metal-surface traverse, denoted as dimensions 2 and 3 in Figure 1, of respectively 10 and 10 mm at one end of the range, may be regarded as appropriate for the impregnating of 12 to 15 ~~g/eg~~ g/m²

substrates at line speeds of up to 10 meters/minute, the shorter metal-surface traverse of 6 and 2 mm is regarded more appropriate for the impregnating of 10 to 13 g/m² substrates at line speeds of 10 meters per minute and greater.

The benefit of these new die arrangements then, as will be shown shortly by way of examples, is to obtain similar casing tube extension properties from paper substrates, which rely more exclusively on resins such as the polyamide epihalohydrin types for their wet strength, rather than on small amounts of these together with the use of regenerated cellulose from viscose, or alternatively of regenerated cellulose from viscose used alone, ~~that.~~ That is because ~~such~~ papers ~~wet strengthened with resins~~ possess inherently less stretch at a given basis weight. ~~And to~~ To compensate for this reduced substrate paper stretch, paper basis weight has been reduced to a level of up to 30 to 40 percent lower, which advantage is lost unless the said paper can be treated in a manner which engenders less machine or longitudinal direction tension during the crucial stages of paper impregnation, viscose penetration of the substrate, coagulation of the cellulose of the viscose and its attendant regeneration. Without the use of the new die arrangement the lighter-weight substrates tend to stretch excessively in their machine directions, particularly for smaller diameter casings running at high line speeds, which has the simultaneous effect of reducing their capacity for stretching in their cross directions.

To understand the effect this has on casing strength one needs to consider the strength parameter of "toughness", alternatively referred to as "Tensile Energy Absorption" for which internationally recognized standards, such as that put out by TAPPI, the Technical Association of the Pulp and Paper ~~industry~~ Industry in the United States of America, under the reference: T494 om-81, and cross referenced with other standards published elsewhere. Simply put the toughness of a material may be defined as the work done when the specimen is stressed to rupture, in tension under prescribed conditions, as measured by the integral of the tensile stress over the range of tensile stretch from zero to maximum strain. It is also clear from a study of the stress-strain properties of the substrate paper of fibrous casings that ~~whilst~~ while the paper possesses a higher tensile strength in its machine, or length direction, compared to its cross direction, the paper may be said to be equally as tough in both directions by virtue of possessing more stretch in its cross compared to ~~its~~ this length direction: that is the areas under their respective stress-strain curves are the same. Classical mechanics demands twice the strength in the hoop of a tube or hose compared to its length direction for good performance and a paper substrate possessing minimum sheet directionality has been the best approximation so far reached with a cellulose-based material, and it is the cross direction strength which is crucially important in a casing for subsequent

meat stuffing and casing expansion purposes. Anything which detracts from maximizing the cross toughness of a casing product, or anything which has the effect of reducing the size ~~exceptions~~ ~~expectations~~ from a given die-paper combination must be deemed to be counter-productive. ~~For And so for~~

these reasons the chief objective of the present application has been to produce casing products as far as possible similar to those in the original specification in terms of their stretch and performance properties but using so-called resin(s) - and viscose plus resin(s), as opposed to viscose-bonded paper substrates, using either dies of the prior art under certain operating conditions or the new die arrangements herein described, with improved performance.

EXAMPLES

Examples will now be presented which describe the tube properties sought. ~~Table 1, and Diagram 1, pages 18 and 19 respectively show how the exceptional casing elasticity properties of VISKO LIGHT products based on abaca paper substrates, wet-strengthened by regenerated cellulose from viscose, together with a small amount of a polyamide epichlorohydrin resin, in the 13,0 to 15,4 g/m² basis weight range, and possessing paper cross direction wet stretch levels in the 9,6 to 13,2% range, are essentially reproduced in casings of similar overall basis weight but based on abaca paper substrates wet-strengthened by resins, without the use of regene-rated~~

Moved to
PP. 32-35
in
Substantial
part

~~cellulose from viscose, which possess cross direction wet stretch levels in the 6,7 to 9,2% but of significantly lower substrate paper basis weights in the 10,2 to 13 g/m² range. Elasticity is here defined as the capacity of the casing, after soaking in water at 40 degree Celsius for minutes, to expand from an uninflated condition to one of 25 inflation by 30 kPa air pressure, expressed as a percentage of the starting size. General-ly speaking two aspects of light weight casing construction are demonstrated by the data of Table 1, viz, that for a given size of casing, casing elasticity follows paper cross direction stretch at the same paper basis 30 weight but that lower paper cross stretch can be compensated by lower paper basis weight to preserve casing elasticity levels when switching from a viscose and/or viscose plus resin(s) bonded to a resin bonded substrate, but not without fully taking into account casing machine tension effects, etc., as described above. Casing burst strengths for the new products based on resin bonded paper compare favorably to those based on viscose bonded paper in terms of strength per unit weight of substrate. Data is collected in Table 2, page 20, to illustrate this: greater absolute strength is obtained for heavier substrate paper, but relative to paper weight, greater burst coefficients are obtained for the lighter substrates. Casing Smoothness properties as determined using the Bendtsen method are shown in Table 3, page 21, for light weight casings produced from viscose plus resin(s) and resin(s) bonded~~

- Moved to
PP.32-35
in
Substantial
part

~~paper substrates. The original specification pointed to significant differences between the Bendtsen smoothness properties of fibrous casings produced in accordance with the then prior art based on heavy weight paper substrates of 17 to 23 g/m², and the lightweight viscose-bonded paper substrates of 13 to 15 g/m², the subject of Table 3A. Whilst the latter showed the lighter weight paper substrates gave rise to casings of smoother inside surfaces compared to those of the prior art, the results of the present application show there are no significant differences between viscose and/or resin(s) bonded paper substrates, in the 11,0 to 14,5 g/m² interval of paper substrate basis weight, incorporated in casings of 64,0 to 74,7 g/m².~~

*- moved to
pp. 32-35
in substantial
part.*

TABLE 1

**CASING ELASTICITY PROPERTIES AS A FUNCTION OF CASING SUBSTRATE
PAPER WEIGHT AND TYPE: VISCOSE PLUS RESIN - VERSUS RESIN(S)-WET
STRENGTHENED**

Casing size, diameter, mm /Paper Bonding Type	Substrate Paper Basis Weight, g/m ²	Paper Wet Cross Direction Stretch, %	Casing Weight g/m ²	Casing Elasticity at 0-30 kPa Inflation
45/Viscose*	13,0 13,0	13,0	74,6	14,6
45/Resin(s)	10,2 13,0 10,2	9,2 74,6 9,2	72,5 14,6 72,5	14,1 14,1
50/Viscose*	13,5 13,5	12,1	70,3	15,3
50/Resin(s)	11,2 12,1 11,2	8,8 70,3 8,8	73,0 15,3 73,0	15,1 15,1

55/Viscose*	13,2 13,2	11.0	72.2	16.7
55/Resin(s)	13,0	7.4	77.4	13.2
55/Resin(s)	10,8 11,0	8.4	73.8	17,5 17,5
	7,4			
	8,4 72,2			
	77,4			
	73,8 16,7			
	13,2 13,0			
	10,8			
60/Viscose*	13,4 13,4	9.6	74.4	17.0
60/Resin(s)	10,7 9,6 10,7	7,8 74,4 7,8	73,6 17,0	17,0 17,0
			73.6	
70/Viscose*	14,9 14,9	11.3	78.2	19.2
70/Resin(s)	12,4 11,3	8,0 78,2 8,0	76,2 19,2	18,3 18,3
	12,4		76.2	
80/Viscose*	15,4 15,4	11.6	74.6	18.5
80/Resin(s)	12,7	8.1	71.5	17.9
80/Resin(s)	15,0 11,6	6.7	82.6	15.7
	8,1			
	6,7 74,6			
	71,5			
	82,6 18,5			
	17,9			
	15,7 12,7			
	15,0			

*Viscose here refers to viscose plus a small amount of a polyamide epihalogenhydrin resin, which resin can be seen not to affect substrate paper cross direction stretch, to an appreciable extent compared to the resin(s) of the exclusively resin(s)-bonded substrates, and indeed the higher values are typical of predominantly viscose-bonded paper whilst the lower typical of paper bonded without viscose.

TABLE 2

**CASING BURST-STRENGTH ELASTICITY PROPERTIES AS A FUNCTION OF
CASING SUBSTRATE PAPER WEIGHT AND TYPE: VISCOSE PLUS RESIN-
VERSUS RESIN(S)-WET STRENGTHENED.**

casing size, diameter (d)mm	paper base weight (w) g/m ²	casing weight g/m ²	casing burst strength (b) kPa	strength quotient (SQ) b/w	burst coefficient SQ . d. pi /100*
45/Viscose*	13.0 13.0	74.6	78	6.0 6.0	8.5 8.5
45/Resin(s)	10.2 74.6 10.2	72.5 72.5	66	6.5 6.5	9.1 9.1
50/Viscose*	13.5 13.5	70.1	77	5.7 5.7	9.0
50/Resin(s)	11.2 70.1 11.2	73.0 73.0	79	7.1 7.1	11.1 11.1
55/Viscose*	13.2 13.2	72.2	71	5.4 5.4	9.3
55/Resin(s)	10.8 72.2 10.8	73.8 73.8	68	6.3 9.3 6.3	10.9 10.9
60/Viscose*	13.4 13.4	74.4	70	5.2 5.2	9.8
60/Resin(s)	10.7 74.4 10.7	73.6 73.6	57	5.3 9.8 5.3	10.0 10.0
70/Viscose*	14.9 14.9	78.2	65	4.4 4.4	9.7
70/Resin(s)	12.4 78.2 12.4	76.2 76.2	53	4.3 9.7 4.3	9.5 9.5
80/Viscose*	15.4 15.4	74.6	54	3.5 3.5	8.8
80/Resin(s)	12.7 74.6 12.7	71.5 71.5	52	4.1 8.8 4.1	10.3 10.3

*Viscose here refers to viscose plus a small amount of a polyamide
epihalogenhydrin resin.

TABLE 3

TUBING SMOOTHNESS PROPERTIES OF SUBJECT LIGHT-WEIGHT TUBINGS: Viscose* versus Resin bonded Substrate Paper				
PRODUCT	BENDTSEN SMOOTHNESS, cm3 air/minute			
diam. mm	Paper Weight, g/m ²	Tube Wt. g/m ²	Inside Surface	Outside Surface
45 resin(s)	11.0 11.0	72.8	750	170
45 viscose*	13.0 72.8 13.0	73.2 73.2	950	190
50 resin(s)	11.0 11.0	67.6	725	155
50 viscose*	13.5 67.6 13.5	64.0 64.0	900	220
55 resin(s)	11.0 11.0	74.7	900	145
55 viscose*	13.5 74.7 13.5	70.0 70.0	850	220
60 resin(s)	12.0 72.7 12.0	72.7	900	125
80 viscose*	14.5 73.1 14.5	73.1	850	160

*Viscose here refers to viscose plus a small amount of a polyamide
epihalogenhydrin resin.

TABLE 3A

PRODUCT	<u>BENDTSEN SMOOTHNESS</u>			<u>cm3 air/minute</u>		
<u>STEM</u>	Subject Tubing				prior Art Tubing	
diameter mm	Weight g/m ²	Inside Surface	Outside Surface	Weight g/m ²	Inside Surface	Outside Surface
45	64,5 64.5	950	200	73,0 73.0	1080	290
50	63,7 63.7	900	220	70,0 70.0	1100	320
55	70,0 70.0	850	220	75,9 75.9	1080	310
80	72,5 72.5	870	220	96,4 96.4	1300	370
50	80,2 80.2	900	200	96,4 96.4	1100	310
105	73,0 73.0	850	160	92,1 92.1	1375	330
120	78,0 78.0	1025	180	96,8 96.8	1600	390

~~The principle of the Bendtsan smoothness test is to measure the amount of air, under a controlled pressure head condition, which can pass between a precision engineered annular ring measuring head placed on the surface whose smoothness is to be determined, whilst the test surface itself is placed in contact with a smooth support surface : such that without a test specimen in place no air is observed to flow, whilst test~~

~~surfaces of ever rougher characteristics are observed to permit the flow of ever greater volumes of air.~~ Table 1 shows how the exceptional casing elasticity properties of products based on abaca paper substrates, wet-strengthened by regenerated cellulose from viscose, together with a small amount of a polyamide epichlorohydrin resin, in the 13.0 to 15.4 g/m² basis weight range, and possessing paper cross direction wet stretch levels in the 9.6 to 13.2% range, are essentially reproduced in casings of similar overall basis weight but based on abaca paper substrate wet-strengthened by resins, without the use of ragene-rated cellulose from viscose, which possess cross direction wet stretch levels of 6.7 to 9.2% but of significantly lower substrate paper basis weights in the 10.2 to 13 g/m² range. Elasticity is here defined as the capacity of the casing, after soaking in water at 40 degree Celsius for minutes, to expand from an uninflated condition to one of inflation by 30 kPa air pressure, expressed as a percentage of the starting size. Generally speaking two aspects of light-weight casing construction are demonstrated by the data of Table 1, viz, that for a given size of casing, casing elasticity follows paper cross direction stretch at the same paper basis weight but that lower paper cross stretch can be compensated by lower paper basis weight to preserve casing elasticity levels when switching from a viscose and/or viscose plus resin(s)-bonded to a resin-bonded substrate, but not without fully taking into account casing machine tension effects, etc.,

Moved
From
PP. 26-28
in Substantial
Part.

as described above. Casing burst strengths for the new products based on resin-bonded paper compare favorably to those based on viscose-bonded paper in terms of strength per unit weight of substrate. Data is collected in Table 2, page 20, to illustrate this: greater absolute strength is obtained for heavier substrate paper, but relative to paper weight, greater burst coefficients are obtained for the lighter substrates.

~~Since the subject materials here are both of a porous nature, of course a component of the air flow will always pass through the test specimen and escape from under the measuring head from beneath the surface of the side in contact with the smooth specimen support, such that a lower flow for the outside surface, obtained above in the case of the subject light-weight tubings, reflects also a smoother inside surface, that is less leakage from the undersurface, than for the example of the prior art: that the latter phenomenon is not related directly to basis weight can be seen by comparing air flows at the same casing basis weights, albeit for different sizes.~~

~~These and more practical manifestations of a tubing possessing a smoother inside surface, such as cleaner release of the untreated cellulose surface from meat proteins, attest to the improved construction of achieved with the subject light-weight tubings~~
Casing smoothness properties as determined using the Bendtsen method are shown in Table 3, page 21, for light-weight casings produced from viscose plus resin(s) and resin(s)-bonded paper

Moved from
PP. 26-28
is substantial
part.

substrates. The original specification pointed to significant differences between the Bendtsen smoothness properties of fibrous casings produced in accordance with the prior art based on heavy-weight paper substrates of 17 to 23 g/m², and the light-weight viscose-bonded paper substrates of 13 to 15 g/m², the subject of Table 3A. While the latter showed the lighter weight paper substrates gave rise to casings of smoother inside surfaces compared to those of the prior art, the results of the present application show there are no significant differences between viscose and/or resin(s)-bonded paper substrates, in the 11.0 to 14.5 g/m² interval of paper substrate basis weight, incorporated in casings of 64.0 to 74.7 g/m².

Moved from
pp. 26-28
in Substantial
part.